

mipa

PROTECTOR

tough – durable – protective



Item no. 20410 0001US

Highly resistant 2K polyurethane-acrylic paint system for scratch resistant, robust and black coating of truck bed surfaces (e.g. Pick-Up truck beds) and for all heavy duty surfaces on commercial vehicles, camping cars, trailers and SUVs, a.s.o.
Mipa Protector is also available as tintable version.

Quality 
made in Germany

mipa

Professional Coating Systems

Mipa USA, Inc. · 13 American Way suite 15 · Spotswood NJ 08884 · Phone: 732-416-9590 · info@mipa-usa.com · www.mipa-usa.com

For professional use only. Before use please see relevant product information, safety data sheet and precautions stated on the product label.

Application



Standard texture through underbody applicator as supplied

1. Apply first a medium wet coat with 29-57 psi (2-4 bar)
2. Subsequent coats can be applied after 10 min. - 1 hour flash-off time.
3. To achieve a coarse texture reduce pressure to 14-21 psi (1-1,5 bar). Distance to the object 1.5-2 foot (45-60 cm)

HLVP gravity feed spray gun: Use nozzle 2.5



Medium texture through underbody applicator as supplied

1. Apply first a medium wet coat with 29-57 psi (2-4 bar)
2. Subsequent coats can be applied after 10 min. - 1 hour flash-off time.
3. To obtain a medium texture reduce pressure to 29 psi (2 bar). Distance to the object 1.5 - 2 foot (45-60 cm)

HLVP gravity feed spray gun: Use nozzle 2.0-2.5



Fine texture through underbody applicator as supplied

1. Apply first a medium wet coat with 29-57 psi (2-4 bar)
2. Subsequent coats can be applied after 5 min. - 1 hour flash-off time.
3. To realize a fine texture apply Mipa Protector with 43-57 psi (3-4 bar). Distance to the object 2 foot (60 cm).

HLVP gravity feed spray gun: Use nozzle 1.6-1.8

To create very fine texture add 10-20% of Mipa ZERO VOC Thinner.

mipa
Professional Coating Systems