Mipa 2K-Elastic

Technical data sheet



Intended use

Additive used to improve the elasticity of Mipa 2K paints (OC, PUR HS, PU 240, PU 257), or Mipa 2K clearcoats. This additive is required to paint deformable plastics.


quantity to add:

basic paint + 10 - 50 % Mipa 2K-Elastic

Mipa 2K-Express-Clearcoat CX 3 can be elastified by adding up to 15 % Mipa 2K-Elastic.

Spreading rate: --

General informations



Version: us 0418
This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on
years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our
products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete
the information content at any time, without prior notice or obligation to update.

MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +49(0)8703/922-0 · Fax: +49(0)8703/922-100 · mipa@mipa-paints.com · www.mipa-paints.com

Mipa 2K-Elastic

Technical data sheet



Version: us 0418

\bigcirc	Drying time object temperature	dust dry 	set to touch 	ready for assembly 	sandable 	recoatable
Note						
Storage:		In tightly closed original containers at least 3 year shelf life. Storage temperature range 50 - 86°F (10 - 30 °C) Protect package from direct sunlight and heat.				
VOC Information:		VOC as packaged: less exempt solvents 485 g/l / 4.0 lb/gl with exempt solvents 485 g/l / 4.0 lb/gl				
		Always check local VOC laws to ensure that the use of Mipa products is compliant in your area.				
Processing conditions:		From 50 °F (10 °C) and up to 80 % relative air humidity. Ensure an adequate supply and exhaust air ventilation.				
General informations:		The addition Mipa 2K-Elastic does not affect the quantity of the hardener to be added. Depending on the added quantity of Mipa 2K-Elastic, the drying time is extended up to 100%. Don't use more than 15% of Mipa 2K Elastic in our Mipa 2K-Express-Clearcoat CX 3. The drying time of Mipa 2K-Express-Clearcoat CX 3 might be slightly extended.				
		Safety aspect: For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts.The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.				
		Medical Response: Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP) US Emergency Phone Number (for transportation incidents only) 1-800-535-5053 (Infotrac)				
		Exclusive Importer: Fleetwood Products 3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.				

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +49(0)8703/922-0 · Fax: +49(0)8703/922-100 · mipa@mipa-paints.com · www.mipa-paints.com