

Intended use

Mipa Brillant-Design are transparent tinting bases which have been especially designed to create particularly brilliant effect coatings on cars and motorcycles. Suitable to tint solvent-based Mipa BC paints and Mipa 2K clearcoats.

Mixing ratio:

See technical data sheet of the paint system which is intended to be used in combination with Mipa Brillant Design. The mixing ratio with is not affected by the addition of Mipa Brillant-Design. The colour shade depends on the applied coat thickness.

Processing:

Mipa Brillant-Design is a solution of dyes which can only be used in combination with a paint system. The addition of Mipa Brillant-Design affects differently the viscosity of various paint qualities. Therefore the spraying viscosity of each paint system must be set with the recommended thinner.

Applied as basecoat:

Maximum addition of Mipa Brillant-Design to Mipa BC 000 colourless: 20 % by weight

Tinting basecoats:

Maximum addition of Mipa Brillant-Design to Mipa BC: 20 % by weight





Tinting clearcoats:






Maximum addition of Mipa Brillant-Design to Mipa 2K-clearcoats 15 % by weight.

Mixed with clearcoats, the transparency of the product is very high.

Spreading rate: –

General informations

	<p>Colour</p> <p>BD 01 yellow BD 03 red BD 05 blue</p>						
	<p>Mixing ratio</p> <table border="0"> <tr> <td>Hardener</td> <td>by weight (lacquer : hardener)</td> <td>by volume (lacquer : hardener)</td> </tr> <tr> <td>–</td> <td>–</td> <td>–</td> </tr> </table>	Hardener	by weight (lacquer : hardener)	by volume (lacquer : hardener)	–	–	–
Hardener	by weight (lacquer : hardener)	by volume (lacquer : hardener)					
–	–	–					
	<p>Hardener</p> <table border="0"> <tr> <td>for complete paintwork</td> <td>for partial paintwork</td> </tr> <tr> <td>–</td> <td>–</td> </tr> </table>	for complete paintwork	for partial paintwork	–	–		
for complete paintwork	for partial paintwork						
–	–						
	<p>Pot life</p> <p>–</p>						

	Thinner --					
	Spray viscosity gravity spray gun	Airmix/Airless				
	Application mode	Hardener	pressure (bar)	nozzle (mm)	spray passes	Thinner
	--	--	--	--	--	--
	Flash-off time --					
Dry coat thickness --						
	Drying time	dust dry	set to touch	ready for assembly	sandable	recoatable
	object temperature	--	--	--	--	--

Note

Storage:

In tightly closed original containers at least 2 years shelf life.
Storage temperature range 50 - 86°F (10 - 30 °C)
Protect package from direct sunlight and heat.

VOC Information:

VOC as packaged:
less exempt solvents 835 g/l / 7.0 lb/gl
with exempt solvents 835 g/l / 7.0 lb/gl

Always check local VOC laws to ensure that the use of Mipa products is compliant in your area.

Processing conditions:

from 50 °F (10 °C) and up to 80 % relative air humidity.
Ensure an adequate supply and exhaust air ventilation.

General informations:

Before the application, test the suitability of Mipa Brillant-Design when you are using other paint systems than those specified. Compatible paint systems are: Mipa BC and Mipa 2K-Clearcoats. When tinting clearcoats with Mipa Brillant-Design, consider that the transparent tinting base has just a limited UV-resistance and you might have to face an early effect loss depending on the UV-exposure. Therefore apply an additional clearcoat layer without Mipa Brillant-Design to ensure the best possible UV-protection. Shake thoroughly before use. Close containers immediately after use.

Safety aspect:

For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts. The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.

Medical Response:

Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP)
US Emergency Phone Number (for transportation incidents only) 1-800-535-5053
(Infotrac)

Exclusive Importer: Fleetwood Products

3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com
fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.