


Intended use

Mipa 2K EP Acellerator reduces the drying time of Mipa 2K epoxy fillers and primers. For example, Mipa EP Multi-Filler HB 2.1 and Mipa EP 164 high build primer. Its use is especially recommended at lower temperatures.

Attention: Pot life is reduced.

Processing instructions



Mixing ratio

by weight (lacquer : acellerator)	by volume (lacquer : hardener)
add at most 3 % to basic paint	--



Hardener

see tech sheet basic product



Pot life

see tech sheet basic product



Thinner

see tech sheet basic product

Note

Storage: at least 2 years in unopened original container

VOC Information: VOC as packaged:
less exempt solvents 0 g/l / 0.0 lb/gl
with exempt solvents 0 g/l / 0.0 lb/gl

Special notes: For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts. The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.

Medical Response:
Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP)
US Emergency Phone Number (for transportation incidents only) 1-800-535-5053 (Infotrac)

Exclusive Importer: Fleetwood Products
3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com
fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.