

Intended use









Mipa Multi-Tint pigment pastes are universal colour pastes used to tint Mipa 1K and 2K products. Mipa Multi-Tint can be used in most solvent-born paint systems (e.g. to tint all Mipa primers and fillers to improve colour shade for better covering of the topcoat).

All pigment pastes are lead free.

Mipa Multi-Tint pigment pastes can be added up to 10 % by weight.

Spreading rate: --

General informations

	Colour oxide yellow, red, blue, green, black					
	Mixing ratio Hardener		by weight (lacquer : hardener)		by volume (lacquer : hardener)	
	--	--	--	--	--	--
	Hardener for complete paintwork				for partial paintwork	
	--	--	--	--	--	--
	Pot life					
	--	--	--	--	--	--
	Thinner					
	--	--	--	--	--	--
	Spray viscosity See tech sheet of tinted product. gravity spray gun				Airmix/Airless	
	--	--	--	--	--	--
	Application mode Application mode	Hardener	pressure (bar)	nozzle (mm)	spray passes	Thinner
	--	--	--	--	--	--
	Flash-off time					
	--	--	--	--	--	--
	Dry coat thickness					
	--	--	--	--	--	--



Drying time
object
temperature

dust dry

set to touch

ready for assembly

sandable

recoatable

--

--

--

--

--

--

Note

Storage:

In tightly closed original containers at least 2 years shelf life.
Storage temperature range 50 - 86°F (10 - 30 °C)
Protect package from direct sunlight and heat.

VOC Information:

VOC as packaged:
less exempt solvents 460 g/l / 3.8 lb/gl
with exempt solvents 460 g/l / 3.8 lb/gl

Always check local VOC laws to ensure that the use of Mipa products is compliant in your area.

Processing conditions:

From 50 °F (+10 °C) and up to 80 % relative air humidity. Ensure an adequate supply and exhaust air ventilation.

General informations:

Mipa Multi Tint Pigment pastes can be used in all solvent-based paint-systems based on alkyd, acryl, PVC, PVB, melamine, polyurethan, epoxide and polyester products.

After adding of maximum 10% by weight agitate thoroughly before adding hardener. Mixing ratio of the tinted product doesn't change.

Using Mipa Multi Tint in a higher concentration of 10 % can influence the quality of the tinted product. E.G. adhesion, sandability or elasticity.

Safety aspect:

For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts. The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.

Medical Response:

Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP)
US Emergency Phone Number (for transportation incidents only) 1-800-535-5053 (Infotrac)

Exclusive Importer: Fleetwood Products

3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com
fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.