









Intended use

Mipa Unterbody WAX is a durable anti-corrosion-protecton for car undersealing, wheel castings, a.s.o. Permanent reliable seasonal protection against de-icing salt. Remains still effective, even applied in thin coats. Perfect adhesion to all kind of substrates, excellent anti corrosion protection, drop free even when applied in high thickness coatings.

Spreading rate: 200 sq.ft/gal (2 m²/l) by 20 mil (500µm)

General informations

	Colour brownish transparent					
	Mixing ratio Hardener		by weight (lacquer : hardener)	by volume (lacquer : hardener)		
	--	--	--	--		
	Hardener for complete paintwork			for partial paintwork		
	--			--		
	Pot life					
	--					
	Thinner					
	--					
	Spray viscosity ready to use gravity spray gun			Airmix/Airless		
	--			--		
	Application mode Application mode	Hardener	pressure (bar)	nozzle (mm)	spray passes	Thinner
	Mipa Unterbody equipment	--	43 - 85 psi (3 - 6 bar)	--	1 - 2	--
	Flash-off time					
	--					
	Dry coat thickness 12 - 20 mil (300 - 500 µm)					



Drying time
object
temperature

dust dry

set to
touch

ready for
assembly

sandable

recoatable

--

--

--

--

--

--

Note

Storage:

In tightly closed original containers at least 3 years shelf life.
Storage temperature range 50 - 86°F (10 - 30 °C)
Protect package from direct sunlight and heat.

VOC Information:

VOC as packaged and applied (ready to spray):
less exempt solvents 417 g/l / 3.5 lb/gl
with exempt solvents 417 g/l / 3.5 lb/gl

Always check local VOC laws to ensure that the use of Mipa products is compliant in your area.

Processing conditions:

from 50 °F (10 °C) and up to 80 % relative air humidity.
Ensure an adequate supply and exhaust air ventilation.

General informations:

Before starting application all necessary precautions should be taken to prevent spraying of the engine, exhaust pipes and the whole brake system.

Substrate must be clean, dry and free from grease, oil and rust. Remove an old underseal which is not in good condition and firmly adhering. Shake can vigorously before use. After application wait 1 hour for flash off.

Safety aspect:

For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts. The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.

Medical Response:

Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP)
US Emergency Phone Number (for transportation incidents only) 1-800-535-5053 (Infotrac)

Exclusive Importer: Fleetwood Products

3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com
fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.