










Intended use

Thinner / reducer for the Mipa WBC mixing system to adjust the required spray viscosity.

Mixing ratio: Mipa WBC 2-Schicht-Basislack + 10-20% Mipa WBC-Thinner

Spreading rate: --

General informations

	Colour colorless					
	Mixing ratio					
	Hardener		by weight (lacquer : hardener)		by volume (lacquer : hardener)	
	--	--	--	--	--	--
	Hardener					
	for complete paintwork				for partial paintwork	
	--	--	--	--	--	--
	Pot life					
	--	--	--	--	--	--
	Thinner					
	--	--	--	--	--	--
	Spray viscosity					
	gravity spray gun				Airmix/Airless	
	--	--	--	--	--	--
	Application mode					
	Application mode	Hardener	pressure (bar)	nozzle (mm)	spray passes	Thinner
	--	--	--	--	--	--
	Flash-off time					
	--	--	--	--	--	--
	Dry coat thickness					
	--	--	--	--	--	--
	Drying time					
	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	--	--	--	--	--	--

Note

Storage: Frost-free storage.

VOC Information: VOC as packaged:
less exempt solvents 0 g/l / 0.0 lb/gal
with exempt solvents 0 g/l / 0.0 lb/gal

Processing conditions: from+ 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

General informations: Frost-free storage.

Safety aspect:

For professional use only. Not for sale to or use by the general public. Before opening the packages be sure you understand the warning Messages on the Labels and Safety Data Sheets of all components since the mixture will have the hazards of all of its parts. The manufacturer recommends the use of an air supplied Respirator when exposed to vapors or spray mist.

Medical Response:

Emergency Medical or Spill Control Information 011 49(0)700 24112112 (MIP)
US Emergency Phone Number (for transportation incidents only) 1-800-535-5053 (Infotrac)

Exclusive Importer: Fleetwood Products
3 American Way, Suite 15, Spotswood, NJ 08884 www.mipa-usa.com
fleetwood@mipa-usa.com. 732-416-9590 Phone, 732-416-9592 Fax.